



FABRIC SPECIFICATION SHEET

Style	FM1DRF	
Construction	Polyester multifilament scrim supported needlefelt	
Colour	White	
Weight	g/m ²	550 ± 20
Thickness	mm	1.9 ± 10%
Air Permeability	dm ³ /dm ² /min @ 20mm H ₂ O	201
Max. Linial Shrinkage	For 240 min @ 170 °C	1.67%
Fibre	100% Virgin Polyester	
Bursting Strength	kg/cm ²	52+
Surface Treatment	Superglaze one side	
Finish	Heat Set	
Max. Operating Temperature	°C	130
Application	Standard polyester needlefelt for reverse-pulse dust collectors and CIP applications	

FM1DRF

Filtercorp International Limited

22-24 Bay Park Place, P O Box 66-080
Beach Haven 0749, Auckland, New Zealand
Ph: (09)481-9999 Fax: (09)483-4355
Email: akld@filtercorp.biz

152 Hazeldean Road
Addington 8024, Christchurch, New Zealand
Ph: (03)377-9200 Fax: (03)377-9212
Email: chch@filtercorp.biz

Web site: <http://www.filtercorp.biz>