



FABRIC SPECIFICATION SHEET

FM6AR

Style	FM6AR	
Construction	Scrim supported Nomex needlefelt	
Colour	Yellow	
Weight	g/m ²	500
Thickness	mm	1.7
Air Permeability	cc/cm ² /sec @ 12.5 mm Wg	18
Scrim	Nomex staple fibre	
Max. Linial Shrinkage	For 90 min @ 240 °C	3%
Fibre	Nomex	
Bursting Strength	kg/cm ²	40
Tensile Strength	kg/5 cm width	MD 100 CD 120
Surface Treatment	Singed one side	
Finish	Heat Set & Acid Resistance	
Max. Operating Temperature	°C	220
Application	Asphalt Plants/Hi Temp	

Filtercorp International Limited

22-24 Bay Park Place, P O Box 66-080
Beach Haven, Auckland, New Zealand
Ph: (09)483-7149 Fax: (09)483-4355
Email: akld@filtercorp.co.nz

152 Hazeldean Road
Addington, Christchurch, New Zealand
Ph: (03)377-9200 Fax: (03)377-9212
Email: chch@filtercorp.co.nz

Web site: <http://www.filtercorp.co.nz>