



FABRIC SPECIFICATION SHEET

FM6G - Armourtex

Style	FM6G - Armourtex	
Construction	Nomex multifilament scrim supported needlefelt with PTFE laminated	
Colour	Yellow	
Weight	g/m ²	550 ± 20
Thickness	mm	1.7 ± 10%
Air Permeability	cc/cm ² /sec @	3.7 - 5.6
Scrim	Spun Nomex	
Max. Linial Shrinkage	For 120 min @	1%
Fibre	Nomex	
Bursting Strength	kg/cm ²	26
Tensile Strength	kg/5 cm width	MD 61 CD 61
Surface Treatment	Heat Set	
Finish	PTFE Laminated	
Max. Operating Temperature	°C	200
Application	Asphalt plants - spray driers, boilers, etc	

Filtercorp International Limited

22-24 Bay Park Place, P O Box 66-080
Beach Haven, Auckland, New Zealand
Ph: (09)483-7149 Fax: (09)483-4355
Email: akld@filtercorp.co.nz

152 Hazeldean Road
Addington, Christchurch, New Zealand
Ph: (03)377-9200 Fax: (03)377-9212
Email: chch@filtercorp.co.nz

Web site: <http://www.filtercorp.co.nz>