



FABRIC SPECIFICATION SHEET

Style	WM7G—Woven Polyester	
Weave Pattern	Sateen	
Construction	Woven—3 x 1 twill	
Colour	white	
Weight	g/m ²	305 ± 10%
Minimum Breaking Strength	Kg/50mm	Warp 138
Thickness	mm	0.54 ± 10%
Air Permeability	cc/cm ² /sec @ 12.5 mm Wg	2.0 - 4.0
Fibre	100% Polyester	
Count / Inch	Warp 78 Welt 65	
Finish	PTFE Laminated	
Operating Temperature	°C	Continuous - 135 Surge - 150 (dry)
Application	A woven media which has proven applications in shaker and static dust collectors, breathers and sifter socks. Particularly in fine dust applications.	

WM7G

Filtercorp International Limited

22-24 Bay Park Place, P O Box 66-080
Beach Haven 0749, Auckland, New Zealand
Ph: (09)481-9999 Fax: (09)483-4355
Email: akld@filtercorp.biz

152 Hazeldean Road
Addington 8024, Christchurch, New Zealand
Ph: (03)377-9200 Fax: (03)377-9212
Email: chch@filtercorp.biz

Web site: <http://www.filtercorp.biz>